



constructive solutions

Conbextra EP10

High strength epoxy resin grout

Uses

Provides a free flowing grout, for use where physical properties and chemical resistance of the hardened grout are of utmost importance. It can be used for injection of static and structural cracks as well as grouting. It is suitable for a wide range of heavy duty applications including:

- Under plate grouting to substantial structural elements.
- Base plate grouting in dynamic load situations such as turbines and other reciprocating machinery.
- Heavy industrial applications in steelworks, refineries chemical plants and electroplating works.
- Structural infill where very high strength is required.
- Rail track applications, to support heavy cranes, or on transporter rails.

Advantages

- **Excellent durability** - high compressive, flexural and tensile strengths ensure a long working life.
- **Cost effective** - high early strength gain promotes minimum downtime and early commissioning of plant.
- **User friendly** - simple, full pack mixing to ensure that the performance characteristics are achieved.
- **Versatile** - suitable for a wide range of loading situations including repetitive dynamic loads.
- **Excellent in service performance** - non-shrink capability ensures full surface to surface contact.
- Non-shrink and hence ensures complete surfaces contact and bond, also ensures that it will resist hydrostatic pressure and block penetration of deleterious substances.
- WRc approval BS6920:1990.

Description

Conbextra EP10 is a solvent free epoxy low viscosity resin grout designed for grouting of gap widths of 0.25 to 10 mm which penetrate deeply into cracks and cavities. It is an all liquid system consisting of base and hardener. The components are supplied in the correct mix proportions designed for whole pack mixing on site.

Specification

Where shown on the contract documents, the epoxy grout shall be Conbextra EP10 supplied by Fosroc. It shall provide good general chemical resistance, and a 7 day compressive strength of at least 93 N/mm².

Properties

Pot life:	60 minutes at 20°C 15 minutes at 40°C
Density:	Approx. 1060 kg/m ³
Tensile strength:	30 N/mm ² at 7 days
Flexural strength:	55 N/mm ² at 7 days
Compressive strength:	55 N/mm ² at 1 day 68 N/mm ² at 3 days 93 N/mm ² at 7 days
Modulus of elasticity: (ASTM C580 7 days)	16 KN/mm ²
Viscosity:	250 Cps at 20°C 100 Cps at 35°C
Specific gravity:	1.04

Instructions for use

Preparation

Under-plate grouting

The unrestrained surface area of the grout must be kept to a minimum. Generally, the gap between the perimeter formwork and the plate edge should not exceed 75 mm on the pouring side and 25 mm on the opposite side. Formwork on the flank sides should be kept tight to the plate edge. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Formwork

The formwork should be constructed to be leak proof as Conbextra EP10 is a free flow grout. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints.

For free flow grout conditions, it is essential to provide a hydrostatic head of grout. To achieve this a feeding hopper should be used - please consult your local Fosroc office for more details.

Foundation surface

This must be free from oil, grease, or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris.

Base plate

If delay is likely before placing steel base plates, it is recommended that the underside and edge are coated with Nitoprime 28 to prevent rust formation and ensure bonding with the Conbextra EP10 grout. All metal surfaces should be cleaned to a bright finish in accordance with Swedish Standard SA 2½ or equal. Nitoprime 28 can be applied directly onto newly cleaned steel surfaces even if they are damp.

Conbextra EP10

Mixing

The entire contents of the hardener can should be poured into the base container and mixed for 2 - 3 minutes or until uniform colour is achieved. Once mixed, the material must be used within the specified pot life (see under Properties). After this time, unused material will have stiffened and should be discarded.

Note: Immediately prior to placement, all surfaces must be dry.

Placing

Ensure that the grout can be placed within its pot life. Continuous grout flow is essential. Sufficient grout must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one. Pouring should be from one side of the void to eliminate air entrapment. The hydrostatic head must be maintained at all times so that a continuous grout front is achieved.

Cleaning

All tools and equipment should be cleaned immediately after use with Fosroc Solvent 102*.

Hot weather working

Whilst the performance of Conbextra EP10 at elevated temperatures is assured, application under such conditions can sometimes be difficult. It is therefore suggested that, for temperatures above 35°C, the following guidelines are used:

- (i) Store unmixed materials in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- (ii) Keep mixing and placing equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- (iii) Try to eliminate application in the middle of the day, and certainly avoid application in direct sunlight.
- (iv) Ensure that there are sufficient operatives available to complete application within the material's pot life.

Limitations

Grouts should not be placed in any unrestrained situation, i.e. base plate plinths, etc. Failure to comply may lead to crack development in the grout.

Estimating

Supply

Conbextra EP10:	5 litre packs
Nitoprime 28:	4 litres packs
Fosroc Solvent 102:	4 litres packs

Coverage

Nitoprime 28:	4 to 6 m ² per litre
----------------------	---------------------------------

Storage

When stored in warehouse conditions below 35°C, Conbextra EP10 will have a shelf life of 12 months.

Precautions

Health and Safety

Some people are sensitive to epoxy resin so gloves and a barrier cream such as Kerodex 71, Rozalex 9, Debba-Wet Work or similar should be used when handling these products. If contact with the resin occurs, it must be removed before it hardens with a resin removing cream such as Kerocleanse 22 or Rozalex 42. Follow by washing with soap and water. Do not use Solvent. The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of clean water and seek medical treatment immediately.

Fire

Nitoprime 28 and Fosroc Solvent 102 are flammable

Flash points

Nitoprime 28:	35°C
Fosroc Solvent 102:	33°C



Fosroc Jordan

Head Office
P.O Box 253,
King Abdullah II Industrial State
Sahab 11512, Jordan

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Regional Offices:

Amman-Khalda Offices: Tel: (06) 535 9562
Amman-Sahab Factory: Tel: (06) 402 2665
Aqaba Showroom: Tel: (03) 205 0061

email: enquiryjordan@fosroc.com

Fax: (06) 535 9563
Fax: (06) 402 9475
Fax: (03) 205 0062