

Conplast UW

Underwater concrete admixture system

Uses

Conplast UW is an admixture system specially designed to allow concrete to be placed underwater. Conplast UW increases the cohesion of concrete mixes and minimises washout enabling concrete to be easily placed under water, and produces well compacted, high quality concrete.

Advantages

- No risk of significant washout of cement paste during placing.
- Removes need for specialist placing equipment
- Allows higher strength and reinforced concrete to be satisfactorily placed underwater.

Description

Conplast UW is a chloride free water soluble polymer supplied as a fine off-white powder. Conplast UW produces a gel in the water paste which surrounds cement particles and protects them from washout.

Properties

Chloride content : Nil to BS 5075

Compacted bulk density of the powder : 0.55 - 0.65

Compatibility with cements : Conplast UW can be used with all types of Portland cements and pozzolans. For advice on special cements, consult Fosroc.

Compatibility with other admixtures: Conplast UW is not generally compatible with other types of admixture. It has been formulated to give good workability and the additional use of a plasticising admixture is not normally recommended. In case it is found necessary to use a plasticiser or other type of admixture, Fosroc should be contacted for advice.

Setting times : Stiffening time of concrete using Conplast UW is retarded by approximately 3 to 5 hours at normal dosages, depending on cement and mix characteristics.

Cement washout : Typically, ordinary concrete can exhibit a washout of up to 30% of the fines content. Using Conplast UW in the same mix, this can be reduced to less than 5%.

Instructions for use

Dosage : The normal dosage of Conplast UW is 0.6 to 1.0% by weight of cement, but will depend on the cement and sand content. Site trials should be carried out to establish the optimum dosage for the mix to be used.

Overdosing : An overdose of double the recommended measure of Conplast UW will result in an increase in the anti-washout properties, significantly increased retardation and strength loss of the concrete.

Mix design : Mix proportions should be designed as for a cohesive pump mix. A slump of at least 180mm is typical. A sand content of 40-50% of the total aggregate weight is recommended. A normal minimum cement content for underwater placing is 400kg/m³. Site /plant trials should be carried out to determine the optimum mix design and workability requirements.

Mixing : When concrete is made using a forced action (Power paddle) mixer Conplast UW should be added towards the end of the mixing cycle. It should be added slowly and with care, mixing should continue for a further 1 - 2 minutes.

When concrete is truck mixed Conplast UW should be added to the concrete after mixing either at the plant if near the site, or at site. Conplast UW should be added slowly into the truck, and mixed for 5 - 10 minutes at high speed. It is essential that truck mixers used are in good condition. Agitator trucks are not suitable. When the concrete is truck mixed it may be necessary to adjust the workability of the concrete after Conplast UW has been added. This may be done with a small amount of additional water or the addition of a suitable plasticiser. The concrete should be constantly agitated until the moment of placing.

Cleaning : Spillages of Conplast UW will gel when in contact with moisture and should therefore be removed in the dry state.

Estimating

Packaging

Conplast UW is supplied in 6kg bags.

Storage

Conplast UW should be stored in its sealed bags, protected from moisture and off the floor. A minimum shelf life of 12 months could then be expected.

Precautions

Health and Safety

Conplast UW has no specific health hazards; it is non toxic but should not be ingested. Any eye contamination should be flushed with clean water and medical advice should be sought.

Conplast UW

Additional information

Technical data and guidance can be provided on a wide range of admixtures and concreting aids including plasticisers, retarders, waterproofs, mould release agents, surface retarders and repair materials.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: +91 44 61304500

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0280

www.fosroc.com