

Fosroc Dekguard AC



constructive solutions

High performance, anti-carbonation, environmentally friendly, one-part protective and decorative coating

Uses

Provides a protection system, to a variety of surfaces exposed to aggressive environments. Typical areas of application include:

- External and internal coating for concrete and masonry
- Anti-carbonation coating for car-parks
- Protective coating for bridge structures, sea walls and coastal environments

Advantages

- **Low cost in service** - due to combination of excellent UV and good chemical resistance properties.
- **Anticarbonation coating** - increases life span of structures under carbonation attack.
- **UV Stable** - will not fade or deteriorate in strong sunlight.
- **Excellent service life** - resistant to chlorides and sulphate ions plus a wide range of chemicals.
- **Environment friendly** - water based product suitable for enclosed areas.

Description

Dekguard AC is a high quality, one component, acrylic ester, protective coating which can be applied to a variety of surfaces, viz. concrete, steel, wood and cured epoxies. It is supplied ready for on-site use and it provides a matt coating.

Specification

The final, corrosion resistant coating shall be Dekguard AC, an acrylic ester, protective coating. The coating shall possess excellent anti-carbonation and UV resistance properties. It shall be compatible with concrete, steel, wood and cured epoxies.

The cured coating shall provide CO₂ diffusion resistance equivalent to not less than 750mm of 30 N/mm² concrete cover or 300 m of air cover (Taywood method).

Properties

Specific gravity	:	1.3
Solids by volume @ 25°C	:	45%
		@ 20°C @ 35°C
Drying time	:	
touch dry		1 hr 0.5 hour
recoatable		7 hours 4hours
full cure		7 days 5 days
Carbon dioxide diffusion resistance -		
Equivalent thickness of air	:	312 metres
(Taywood method)		
Carbon dioxide diffusion resistance		
Equivalent thickness of 30N conc.	:	780 mm
(Taywood method)		
Salt fog spray resistance	:	5000 hours
(ASTM B117)		- no change

Chemical resistance :

Fully cured coatings were tested on some common chemicals. Tests were performed by constant immersion, followed by visual inspection (ASTM D1308 method)

Acids (m/v)

Acetic acid 20%	:	Excellent
Lactic acid 20%	:	Excellent
Nitric Acid 5%	:	Excellent
Oleic acid ¹	:	Good

Aqueous solutions

Magnesium Sulphate 25%	:	Excellent
Tap Water	:	Excellent
Sea Water	:	Excellent
Ground Water	:	Excellent
High sulphate water	:	Excellent
Distilled water	:	Excellent

(1) Note - acceptable performance up to 7 days immersion

Consult the local Fosroc office for specific recommendations to meet varying operating conditions.

Fosroc Dekguard AC

Instructions for use

Surface preparation

All surfaces to be treated with Dekguard AC should be clean and free from dust or other loose material.

Concrete surfaces

All surface laitance should be removed by grinding, grit blasting or water jetting, to provide a suitable key. The general standard of surface preparation should be in accordance with ACI 503R-89, Chapter 5, Paragraph 5.4.

Following the preparation of a concrete surface, care should be taken to ensure that any surface irregularities are filled with the appropriate Renderoc* product.

Metal surfaces

Any metal surfaces should be blasted to a bright finish, meeting the requirements of Swedish Standard SA 2½ or equal.

Fully cured epoxies

Please contact your local Fosroc office for details on surface preparation required for existing epoxy coatings.

Priming

For metal and wood substrates, priming is not necessary.

For low-porosity/good quality concrete, pre-soaking of the substrate must be completed using potable water. Saturate the substrate for at least 15mins with water leaving the substrate in a saturated surface-dry(SSD) condition. If concrete surface is found to be porous after pre-soaking, apply a coat of Dekguard Primer Sealer. Dilute the primer 1:10 with water, apply by brush and allow to penetrate and dry. A second coat may be required depending on the substrate porosity.

For friable/very porous substrates priming with Dekguard Primer WB or Dekguard Primer AC is recommended to stabilise the substrate.

Mixing

The contents should be thoroughly stirred to disperse any possible settlement.

Application

Hand application

This can be suitably achieved by brush or roller.

Two coat application, at a rate of 0.2 litres per square meter per coat to achieve a minimum wft of 200 microns. The second coat should be applied only after the first coat has been cured and before 24 hours.

Spray application

Faster rates of application are possible using airless spray equipment, but the local Fosroc office should be contacted prior to application for technical advice.

Cleaning

Tools and equipment should be cleaned with Fosroc Solvent 102* immediately after use.

Repairing and overcoating

Any applications of Dekguard AC which have become damaged can be readily overcoated.

The existing surface should be well abraded, using a stiff wire brush, or similar, to ensure that a good mechanical bond will be achieved between the two layers.

Overcoating works can then proceed as for new work.

Estimating

Supply

Dekguard AC	: 20 litre pails
Dekguard Primer AC	: 20 and 200 litre pails
Dekguard Primer WB	: 20 litre pails
Dekguard Primer Sealer	: 4 litre pails

Coverage

The coverage figures quoted are theoretical, and based upon application to a properly prepared substrate.

Since application conditions vary greatly; due to substrate porosity, quality of surface preparation, application thickness and wastage factors, the on-site figures may vary from those shown below.

Dekguard AC	: 5 m ² /litre @ 200micron wft/coat
	: (2 coat application recommended)
Dekguard Primer AC	: 8 - 10m ² /litre
Dekguard Primer WB	: 8 - 10m ² /litre
Dekguard Primer Sealer	: 50m ² /litre
	diluted 1 to 10



Fosroc Dekguard AC

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Limitations

- A minimum application temperature of 10°C should be observed at all times.

Precautions

Health and safety

Dekguard AC should not come in contact with skin or eyes, nor should they be swallowed.

Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye/face protection. Barrier creams such as Kerodex Antisolvent or Rozalex Antipaint provide additional skin protection.

Should accidental skin contact occur, remove immediately with a resin removing cream such as Kerocleanse Standard Grade Skin Cleanser or Rozaklens Industrial Skin Cleanser, followed by washing with soap and water - **do not** use solvent.

In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

If swallowed seek medical attention immediately - **do not** induce vomiting.

For further information, please consult the Material Safety Data Sheet for Dekguard AC.

Fire

Dekguard AC and Dekguard Primer WB are non flammable.

Dekguard Primer AC is flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO₂ or Foam. Do not use a water jet.

Flash Points

Dekguard Primer AC : 38°C

Storage

Shelf life

All products have a shelf life of 6 months, when stored in warehouse conditions between 10 and 25°C.

Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc Co. LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com

