



Nitoflor SL3000

Flow applied medium to heavy duty epoxy floor topping

Description

Nitoflor SL3000 is a medium-heavy duty, flow applied epoxy floor topping system designed with the highest order of durability to resist abrasion, chemical attack and other physical aggression.

Typical application areas include food and beverage production, dairy processing, pharmaceutical and engineering process areas.

Advantages

- Ease of application
- Non Taint
- Easy to clean
- Seamless
- Tough, high resistance to damage

Specification

Flow applied epoxy floor topping

The designated floor area shall be surfaced with Nitoflor SL3000, a 3 mm thick flow-applied epoxy resin floor topping. The topping shall achieve a compressive strength of 67 N/mm² as per ASTM C579 and a flexural strength of >25 N/mm² at 7 days and tensile strength of > 12 N/mm² when tested as per BS6319 at 27°C. It shall be capable of accepting foot traffic at 24 hours and vehicular traffic at 48 hours.

Standards compliance

Nitoflor SL3000 complies to IS 4631:2001.

Properties

The values given below are average figures achieved in laboratory tests. Actual values obtained on site may show minor variations from those quoted.

Pot Life	@ 27°C
Nitoflor SL3000	: > 45 mins
Nitoprime 25	: 2 - 3 hours
Cure time -	
Foot traffic	: 24 hours
Vehicular traffic	: 48 hours
Chemical resistance	: 7 days
Physical properties	
Mixed density	: 1.85 ± 0.05 g/cc
Compressive strength	
@ 7 days (ASTM C579)	: > 67N/mm ²
Flexural strength	
@ 7 days (BS 6319, part 3)	: > 25N/mm ²
Shore D Hardness	
(ASTM D2240)	: >70
Tensile strength	
@7 days (BS 6319, part 7)	: > 12N/mm ²
Pull of Adhesion strength	
(ASTM D4541) @ 7days	: > 3 N/mm ²



GreenPro Ecolabel Certified by CII

Abrasion Resistance

(ASTM D 4060) : 0.081 mg/cycle loss of weight (with CS 17 wheel of 1000g weight)

Water absorption

(ASTM C413) : Nil

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions. The slip resistance figures given above are affected by application techniques and prevailing site conditions. Slip resistance can reduce over time due to poor maintenance, general wear or surface contaminants.

Nitoflor SL3000 has excellent resistance at ambient temperatures to a wide range of industrial chemicals. Specific data is available on request. Note that it is especially important that spillage is cleaned up quickly and not allowed to dry since much higher concentrations of chemicals may occur on evaporation.

Design criteria

Nitoflor SL3000 is designed for application at a nominal thickness of 3 mm.

Substrates should be dry and not suffer, or be likely to suffer, from rising damp. If necessary, suitable damp-proof membranes should be installed during construction to prevent this. Substrates should not have a relative humidity greater than 75% at the time of installation.

Instructions for use

Nitoflor SL3000 should be applied by specialist contractors who must follow the procedures laid down in the Product Method Statement. Fosroc works with a network of such applicators who have been trained in the correct installation procedures. The following steps are involved in the application which would normally take place over a 2 to 3 day period

Surface Preparation

It is essential that Nitoflor SL3000 is applied to sound, clean and dry surfaces in order that maximum bond strength is achieved between the substrate and the flooring system. All dust and debris should be removed prior to application of the product or its primer.

Nitoflor SL3000

New concrete floors

New concrete, or cementitious substrates, should be at least 28 days old and have a moisture content not exceeding 5%. Laitance deposits on new concrete are best removed by light grit blasting, mechanical scrubbing or grinding.

Old concrete floors

Existing concrete floors which require refurbishment must be prepared to ensure a strong adhesive bond between the flooring system and the existing floor. Mechanical cleaning methods are strongly recommended particularly where heavy contamination by oil and grease has occurred or existing coatings are present. To ensure adhesion, all contamination should be removed. Alternatively, blasting techniques can be used to provide the required substrate.

Priming

All surfaces treated with Nitoflor SL3000 should be primed with Nitoprime 25, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates.

Add the entire contents of the hardener tin to the base tin and mix the two primer components thoroughly for at least 2 minutes - under no circumstances should part mixing be considered.

Once mixed, the primer should be applied immediately to the prepared substrate using stiff brushes and/or rollers. The primer should be well 'scrubbed' into the substrate to ensure full coverage, but care should be taken to avoid over unsightly application or 'ponding'.

Allow the primer to dry (see table below) before proceeding to the next stage. Do not proceed whilst the primer is 'tacky' as this will lead to unsightly marks in the finished surface.

Porous substrates may require a second primer coat - when the first coat is directly absorbed into the substrate - but minimum overcoating times must still be observed (see table below).

The minimum overcoating times will vary slightly according to the porosity of the substrate. However, they should be in accordance with the following ambient application temperatures.

20°C	:	8-12 hours
30°C	:	6-8 hours
40°C	:	4-6 hours

Mixing

Nitoflor SL 3000 flooring is supplied in four pre-weighed packs (base, hardener, aggregate and colour pack) which are ready for immediate on-site use. Part mixing of these components is not acceptable and will affect both performance and appearance of the finished floor.

Mixing should be carried out using either a forced action mixer; or a heavy duty, slow-speed drill with proprietary mixing paddle attachment. All such equipment should be of a type and capacity approved by Fosroc. The components should be mixed in a suitably sized mixing vessel.

The colour pack should be added to the base container and mixed for 15-30 seconds, until homogeneous. Then add the hardener and mix for further 30 seconds, until an even colour and texture is obtained.

Thereafter, the contents of the graded aggregate pack should be slowly added and mixing carried out for a further 3 minutes until a completely homogenous material is obtained.

Application

The applicator should ensure that there are sufficient supplies of plant, labour and materials to make the mixing and subsequent application process a continuous one for any given, independent floor area.

Once mixed, the material must be used within its specified pot life - see "Properties" section.

The material should be poured onto the prepared and primed substrate as soon as mixing is complete. It should be spread to the required thickness preferably using a serrated trowel; with care taken not to overwork the resin, spreading evenly and slowly.

Immediately after laying, the material should be rolled, using a spiked nylon roller, to remove slight trowel marks, and to assist air release. The rolling should be carried out using a 'back and forth' technique along the same path. An overlap of 50% with adjacent paths is recommended.

The rolling process should continue for a minimum of 5 times on the same path, but should be prior to setting of the product.

Floor Joints

All existing expansion or movement joints should be followed through the new floor surface.

Joint sealant & joint geometry should be compatible with the floor type used, intended exposure conditions and likely movement characteristics of the substrate - consult the local Fosroc office for more details.



Nitoflor SL3000

Cleaning

Nitoprime 25 and Nitoflor SL3000 should be removed from tools and equipment with Nitoflor Sol immediately after use. Hardened material can only be removed mechanically.

Maintenance

The service life of a floor can be considerably extended by good housekeeping. Regular cleaning may be carried out using a rotary scrubbing machine with a water miscible cleaning agent at temperatures up to 50°C.

Technical support

Fosroc offers a comprehensive range of high performance, high quality, flooring, jointing and repair products for both new and existing floor surfaces. In addition, the company offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Limitations

- Nitoflor SL3000 should not be applied on to surfaces known to, or likely to suffer from, rising dampness, potential osmosis problems or have a relative humidity greater than 75% as measured in accordance with BS 8203 Appendix A, or by Protimeter.
- In areas where significant thermal shock is likely to occur, please consult the local Fosroc office.
- Nitoflor SL3000 should not be applied to asphalt, weak or friable concrete, unmodified sand/cement screeds, PVC tiles or sheet.

For information on other substrates, consult the local Fosroc office.
- Nitoflor SL3000 should not be installed at temperatures below 10°C or above 45°C.
- In common with all epoxy materials some light shade changes may be experienced over the long term when placed in adverse conditions. Any such change in shade is not regarded as being detrimental to performance.

Estimating

Supply

Nitoflor SL3000 : 15 litre packs

	Including colour packs
Nitoprime 25	: 1 and 4 litre packs
Nitoflor Sol	: 5 litre and 20 litre tins

Coverage

Nitoflor SL3000	: 5.0 m ² /pack @ 3 mm thickness
Nitoprime 25	: 5.5 - 6.5 m ² /litre

Note : The coverage figures given are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced. Typically, an additional 10% should be allowed for surface irregularities and wastage although this will vary with site conditions.

Storage

Shelf life

Nitoflor SL3000 has a shelf life of 12 months if kept in warehouse conditions at 30°C in the original, unopened pack.

Storage conditions

Store in dry conditions between 5°C and 30°C, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures the shelf life will be reduced.

Disposal

All cementitious products and Inert epoxy fillers can be used for landfilling. Any left out of epoxy base and hardener (expired or small bottom quantity) before disposing to empty cans/tins/pail buckets, take out the material and mix both base and hardener, make it solid and then dispose through authorized PCB vendor. Used empty epoxy Base & Hardener pail buckets/Tins, (Ensure completely drained out the material) dispose through approved vendor only.

Precautions

Health and safety

Nitoflor SL3000, Nitoprime 25, Nitoprime 28 and Nitoflor Sol should not come in contact with the skin and eyes, or be swallowed.

Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent.

In case of contact with eyes, rinse immediately with plenty



Nitoflor SL3000

of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Fire

Nitoprime 25 and Nitoflor Sol are flammable. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO₂ or foam. Do not use a water jet.

Nitoflor SL3000 is non-flammable.

Flash points

Nitoprime 25 : 39°C

Nitoflor Sol : 33°C

Do's and Don'ts

Do's

- Cleaning regularly with Mop and Soft washing agent or with soft mopping device.
- Trolley and Forklift movement with rubber or Teflon wheel
- All normal activity without any mechanical damage of the floor.
- Consult with manufacturer if any cut to be made over the floor
- Clean the floor immediately, if any strong chemical or hot liquid fall on the floor.

Don'ts

- Use any Harsh chemicals, acid base or any cleaning solution without confirming the manufacturer
- Dragging of sharp, heavy object and trolley with metal wheel

- Allow any Impact with heavy object on the floor
- Carry out any hot activity like welding or with any activity which create fire
- Drill or core cutting without confirmation from manufacturer
- Make it expose to high temperature > 60°C

Additional information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult our local Fosroc office - as below.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector-62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278