



Nitoprime 25

Epoxy resin primer for Fosroc flooring and coating range

Uses

Nitoprime 25 is a general purpose anti-corrosion primer for concrete and steel surfaces (prepared by abrasive blast cleaning), for use with various Fosroc coatings and flooring range. The product actively prevents corrosion and is tolerant to application over manually prepared surfaces.

Advantages

- Active corrosion control
- Formulated for use with Fosroc flooring and coating systems

Description

Nitoprime 25 is a two pack epoxy primer, providing corrosion protection and improved adhesion.

Properties

	23°C	35°C
Pot Life	: 2h	1h
Average Drying Times	:	
Touch	: 4-5h	3h
Recoat	: 6-8h	4h
To handle	: 9-10h	6h

Instructions to use

Surface preparation

Blast clean to SA2½ BS7079: Part A1:1989 (ISO 8501-1:1988). Average surface profile should be in the range of 50-75µm. Manually prepared surfaces should be to a minimum standard of St 3 BS7079: Part A1:1989 at the time of coating. Ensure surfaces to be coated are dry and free from all traces of surface contaminants.

Application

Equipment

Airless Spray

	wft 75-125mm	wft 125-350mm
Nozzle Size	: 0.33-0.38mm (13-15thou)	0.38-0.46mm (15-18thou)
Fan Angle	: 40°C	40°C

Operating Pressure	: 155kg/cm ² (2200psi)	155kg/cm ² (2200psi)
---------------------------	--------------------------------------	------------------------------------

The airless spray details given above are intended as a guide only. Fluid hose length and diameter, paint temperature and project complexity all have an effect on the choice of spray tip and operating pressure. The operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions vary, it is the applicators' responsibility to ensure that the equipment in use has been adjusted to give optimum performance.

Conventional spray

Nozzle Size	: 1.27mm (50 thou)
Atomising Pressure	: 2.8kg/cm ² (40psi)
Fluid pressure	: 0.4kg/cm ² (6psi)

The conventional spray details given above are intended as a guide only. It may be found that in some circumstances, slight variations in atomising pressure, fluid pressure and alteration of tip arrangements may provide optimum atomisation.

For application by conventional spray, thinning with up to 10% Fosroc Solvent 102 may be required. Adjustment for wet film thickness should be allowed. Thinning will effect VOC compliance.

Brush and Roller

The material is suitable for brush and roller application.

Application of more than one coat may be required to give the equivalent dry film thickness to one spray applied coat.

Application conditions

The application of Nitoprime 25 must take place immediately to a dry steel surface after completion of the preparation work. Good ventillation is essential in conditions of high humidity, i.e 80-85%.

Limitations

- Nitoprime 25 should not be applied when the substrate temperature is below 5°C or is 5°C and falling. If any doubt arises concerning temperature or application conditions, consult the local Fosroc office..

Nitoprime 25

Estimating

Supply

Nitoprime 25	: 5 KG
Fosroc Solvent 102	: 5 litre cans

Coverage

Nitoprime 25	: 4 – 5 m ² /kg @ 133microns wft
--------------	--

Note : The coverage figure of Nitoprime 25 is theoretical and may vary due to a variety of site conditions.

Storage

Shelf life

Nitoprime 25 has a shelf life of 12 months and Fosroc Solvent 102 has a shelf life of 12 months, if kept in a dry store in the original unopened packs.

Precautions

Health and safety

Nitoprime 25 and Fosroc Solvent 102 should not come in contact with skin or eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection.

If working in confined areas, suitable respiratory equipment must be used.

The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of skin contact with Nitoprime 25, remove immediately with resin removing cream followed by washing with soap and water.

Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

Fire

Nitoprime 25 and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO₂ or foam. Do not use a water jet.

Flash points

Fosroc Solvent 102	: 33 °C
Nitoprime 25	: 24 °C

FOSROC



PT.FOSROC

Indonesia

Jl.Akasia II Blok A8 No.1
Delta Silicon Industrial Park
Lippo Cikarang
Bekasi 17550
Indonesia

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+62 21 897 2103-06

fax:
+62 21 897 2107

email:
Indonesia@Fosroc.com