

Fosroc Nitoseal MS600



constructive solutions

One part, civil engineering sealant

Uses

Nitoseal MS600 is suitable for sealing movement joints in buildings and civil engineering structures including joints that will be subject to intermittent immersion.

Typical applications include:

- Reservoirs
- Sewage tanks
- Sea walls
- Basements
- Subways
- Parapets
- Bridges
- Superstructures

Advantages

- Approved for use in contact with potable water
- Meets key international standards
- Resistant to aerobic and anaerobic bacteriological attack
- Excellent resistance to dilute acids and alkalis
- Cures to a tough, elastic rubber seal
- Accommodates continuous and pronounced cyclic movement
- High resistance to ageing, reduces physical damage due to climatic extremes
- Single component yet fast rate of cure
- Can be applied to damp substrates
- Isocyanate free technology

Description

Nitoseal MS600 is a one part medium modulus sealant based on hybrid silyl modified polyether technology. It has a fast rate of cure and forms a tough, highly durable and water resistant elastomer. Conforms to the Water supply(water quality) Regulations 2000 & 2001 Regulations 31(4b) for products having a small surface area in contact with water for public supply.

Properties

Form : Smooth, non-slumping paste

Solids content : 100%

Colour : Grey, Portland stone
For other colours contact
Fosroc for further Information

MAF (Movement : 25% butt joints

Accommodation : 50% lap joints

Factor

Skinning time at

20 C / 50% RH : 30 minutes

Cure rate at : 24 hours: 3mm

20 C / 50% RH : 48 hours: 6mm

72 hours: 8mm

Application

Temperature : 5°C to 50°C

Service : Dry : -30°C to +80°C

temperature : Wet: up to 60°C

Hardness shore'A' : 32

(@ 20°C)

Chemical : Resistant to occasional spillage
resistance : many chemicals.

Biological : Nitoseal MS600 has been
resistance : evaluated in microbiologically
active situations and has been
shown to have resistance to
aerobic and anaerobic conditions
and has Anti Fungul resistance

UV resistance : Excellent

Standards compliance

Nitoseal MS600 is approved for use in contact with potable water and meets the requirements of BS6920. Part 1 2000, WRAS listed product.

Conforms with the performance criteria of BS4254 (1991) and ASTM C920-94:type S, grade NS, Class 25 and ASTM C793 after accelerated weathering.



Nitoseal MS a name you'll
want to stick
with.



Fosroc Nitoseal MS600

Design criteria

Nitoseal MS600 should be applied to joints between 5 and 50mm wide. Joints which are expected to experience cyclic movements should be designed to an optimum width : depth ratio of 2:1, subject to the overriding recommended minimum sealant depths set out below: 5mm for metals, glass and other non-porous surfaces; 8mm for all porous surfaces; 20mm for joints subject to hydrostatic pressure.

To ensure that the sealant remains within its stated movement capacity (25% MAF), sealing slot widths should be designed in accordance with the recommendations of BS 6093.1993. The Movement Accommodation Factor is a figure quoted indicating the ability of a sealant to accommodate joint movement throughout the service life of that sealant, expressed as a percentage of the joint width at time of sealing.

To calculate the theoretical minimum joint width knowing the expected maximum working movement of the joint:

$$W = \frac{M}{MAF/100} + M$$

W = Joint width

M = Expected maximum working movement of joint

MAF = Movement Accommodation Factor of that sealant

Instructions to use

Preparation

Joint surfaces must be clean, dry and free from frost. Remove all dirt, laitance, loose material and foreign matter. Remove all rust, scale and protective lacquers from metal surfaces. Removal can be achieved by rigorous wire brushing, grinding or grit blasting.

Joints in concrete should preferably be sawn. After sawing, all saw slurry must be flushed away and the joint allowed to dry.

When resealing, the existing sealant should be removed from the joint and the arris cleaned back to sound clean concrete. All debris should be removed.

Any expansion joint filler must be checked to ensure it is tightly packed and no gaps or voids exist at the base of the sealing slot before positioning a bond breaker.

The use of a bond breaker is not required in expansion joints containing cellular polyethylene joint filler such as Hydrocell XL or Expandafoam. For construction or contraction joints a bond breaker tape or back-up strip should be used.

Where a particularly neat finish is required, mask the face edges of the joint before sealing and remove immediately after tooling is completed.

Priming

Fosroc Primer MS2 is required for joints that are to be intermittently or permanently immersed or where the substrate is likely to saturated.

When using a primer, empty the entire contents of the hardener tin into the base tin and replace the base tin lid. Mix thoroughly by shaking for at least 2 minutes. Prime the joint face using a clean, dry brush. Avoid over application of primer causing puddles in the bottom of the joint.

Nitoseal MS600 should be applied between 30 minutes and 2 hours after priming.

If a joint is left unsealed for more than 2 hours, the primer should be removed by grit blasting or grinding and the joint re-primed.

Do not split packs of Fosroc Primer MS2.

Application and finishing

Cut the end off the sachet and place in the Fosroc GX gun. Fit the nozzle and cut at 45 degrees at a suitable size for sealing the joint.

Extrude the sealant firmly in to the joint. Tool flush within 5 minutes of application to ensure good contact between the sealant and the substrate.

Cleaning

Clean tools immediately after use with Fosroc Equipment Cleaner. Clean hands with a proprietary hand cleaner.



Fosroc Nitoseal MS600

Limitations

- Should not be applied at temperatures below 5°C
- Not suitable for contact with bituminous materials
- Not suitable for contact with solvents, oil or petrol
- Whilst Nitoseal MS600 has excellent adhesion to many types of residual sealant, its use should not be considered a substitute for a good standard of joint preparation
- Should be fully cured prior to use

Estimating

Supply

Nitoseal MS600 : 10 no x 600ml sachets per box

Fosroc Primer MS2 : 200 ml packs

Guide to quantities

Joint size	Litres per metre run	Metre run per 600 ml sachet
6 x 10	0.06	10.00
12 x 10	0.12	5.00
20 x 20	0.40	1.50
25 x 12	0.30	2.00
30 x 15	0.45	1.33

0.2 litres of Fosroc Primer MS2 will be sufficient for 25m of joint. No allowance has been made for joint size or wastage.

Precautions

Health and safety

Nitoseal MS600 is considered safe in normal use. However, as with any material, good hygiene practices should be followed i.e. keep out of eyes, do not consume, keep away from children and pets and wash hands thoroughly after use.

Storage

Shelf life 12 months.

Storage conditions

Store in original packaging in cool, dry conditions. Storage outside of these conditions may reduce shelf life.



Fosroc Nitoseal MS600

Additional information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the recent version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

