



Nitotile Epoxy Grout

Epoxy resin, chemically resistant tile grout

Uses

To provide a hard wearing, easily cleaned, attractive tile grout where high resistance to chemical attack is required.

Advantages

- Excellent resistance to industrial chemicals
- Solvent free - can be used in confined areas
- Attractive appearance, easily cleaned
- Available in a range of attractive colours
- Low odour formulation

Description

Nitotile Epoxy Grout consists of a blend of specially selected resins, curing agents, graded inert acid resistant fillers and a unique colour pack system.

Properties

Typical properties of mixed material.

	20°C	30°C
Pot life	60 mins	30 mins
Initial Cure	24 hrs	18 hrs
Full Cure	7 days	4 days

Chemical resistance

Nitotile Epoxy Grout is resistant to a comprehensive range of chemicals commonly encountered in industrial applications, few of them are listed below:

Acids

Hydrochloric acid 50%	: Excellent
Nitric acid 25%	: Excellent
Sulphuric acid 50%	: Excellent
Phosphoric acid 50%	: Excellent
Acetic acid 10%	: Excellent
Lactic acid 10%	: Excellent
Citric acid	: Excellent

Alkali

Sodium Hydroxide 50%	: Excellent
Ammonia (880) 10%	: Excellent

Solvents

Petrol, Oil, Kerosene	: Excellent
Butanol	: Very Good
Skydrol	: Good

Other Solutions

Bleach (Conc)	: Excellent
Saturated Sugar	Excellent
Urea	: Excellent

Nitotile Epoxy Grout has been formulated specifically to provide the highest chemical resistance. However at elevated temperatures or where a mixture of chemicals is involved the effects may differ from those found in laboratory tests as described above. For further information, please contact Fosroc.

Instructions for use

Preparation

Joints to be grouted should be clean and free from any dust or debris. Porous tile edges should be primed with Nitoprime 25 or Nitoprime 31.

Mixing

The base and hardener components should be individually stirred to disperse any settlement which may have occurred. Base, hardener and colour pack should then be mixed together in a suitable container until a uniform colour is obtained.

The filler component should then be added to the mixed liquid and blended using a slow speed drill and suitable mixing paddle until a uniform, homogeneous mixture is obtained.

Application

Apply Nitotile Epoxy Grout with a spatula to the spaces between the tiles working the mixture into the joints and around the edges.

Remove surplus material from the face of the tiles with a dry cloth, it may be necessary to use small quantities of Fosroc Solvent 102 to assist in the cleaning process.

Nitotile Epoxy Grout

Cleaning

Nitotile Epoxy Grout should be removed from tools equipment and mixers with Fosroc Solvent 102 immediately after use. Cured material can only be removed mechanically.

Limitations

Nitotile Epoxy Grout should not be exposed to moving water during application.

Estimating

Supply

Nitotile Epoxy Grout	:	3 litre pack
----------------------	---	--------------

Yield

Nitotile Epoxy Grout	:	0.25 litres/m ²
----------------------	---	----------------------------

Storage

Shelf life

Nitotile Epoxy Grout has a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperature and/or high humidity conditions the shelf life may be reduced to 4 to 6 months.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Precautions

Health and safety

Nitotile Epoxy Grout is epoxy resin based. Direct contact with eyes will cause irritation and may cause serious damage if left untreated.

Any eye contamination should be washed immediately with clean water and immediate medical attention sought. Gloves and barrier cream such as Kerodex 71 or Rozalex 9 should be used at all times when handling Nitotile Epoxy Grout.

If contact with the skin occurs a resin removing cream such as Kerocleanse 22 or Rozalex 42 should be used followed by washing with soap and water.



Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8
Seksyen 33, 40400 Shah Alam
Selangor, Malaysia.

Branch Office:

29, Jalan Zainal Abidin,
10400 Penang, Malaysia.

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+60 3 5191 5660

fax:
+60 3 5191 6960

email:
enquiry@malaysia.fosroc.com

+60 4 2287 464

+60 4 2292 661



www.fosroc.com